

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 7 : G03G 5/07, C08K 5/3417, 5/32, 5/23		(11) International Publication Number: WO 00/49465
A1		(43) International Publication Date: 24 August 2000 (24.08.00)
(21) International Application Number: PCT/AU00/00117		(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).
(22) International Filing Date: 16 February 2000 (16.02.00)		
(30) Priority Data: PP 8738 17 February 1999 (17.02.99) AU PQ 3413 14 October 1999 (14.10.99) AU		
(71) Applicant (for all designated States except US): VICTORIA UNIVERSITY OF TECHNOLOGY [AU/AU]; Level 6, Building K, Cnr Ballarat Road And Mills Close, Footscray, VIC 3011 (AU).		
(72) Inventors; and (75) Inventors/Applicants (for US only): GU, Min [AU/AU]; 4 Maverick Close, Doncaster, VIC 3108 (AU). DAY, Daniel, John [AU/AU]; 7/100 Curzon Street, North Melbourne, VIC 3051 (AU). SMALLRIDGE, Andrew, John [AU/AU]; 3 Melosa Avenue, East Brighton, VIC 3187 (AU).		
(74) Agent: FREEHILLS CARTER SMITH & BEADLE; 101 Collins Street, Melbourne, VIC 3000 (AU).		

Published


With international search report.

With amended claims.

(54) Title: ERASABLE/REWRITABLE OPTICAL DATA STORAGE WITH PHOTOREFRACTIVE POLYMERS

(57) Abstract

A method of erasable/rewritable optical data storage is provided in which a laser beam from a laser (10) operated in either a pulsed or continuous wave mode is focussed by an optical system (11-18) onto a photorefractive polymeric material (32) to cause two photon excitation of the material to record data which may subsequently be erased by illuminating the material with radiation having a wavelength in the ultraviolet or visible spectrum to erase the recorded data. New photorefractive polymeric materials having a relatively narrow absorption band for use in the method are also disclosed.



FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

ERASABLE/REWRITABLE OPTICAL DATA STORAGE WITH PHOTOREFRACTIVE POLYMERS

— This invention relates to optical data storage and more particularly to erasable/rewritable three-dimensional optical data storage with photorefractive polymers.

Multi-layered (or three-dimensional) optical memories have increasingly become a field of interest in the development of high-density optical data storage devices. Systems that utilise multiple layer recording can achieve recording densities from 100 to 10,000 times higher than conventional optical data storage devices.

The use of two-photon excitation in three-dimensional (3D) bit optical data storage has grown due to its ability to increase the density in a given material by reducing the volume of the recorded bit. The probability of two-photon excitation is proportional to the squared intensity of the incident light; this effect produces excitation only within a small region of the focus spot. As a result there is less cross talk between neighbouring data layers. Another advantage of two-photon excitation is the reduction of multiple scattering because of the utilisation of an illumination beam of an infrared wavelength, so that more layers can be recorded along the depth of a volume material.

Over the years different materials have been used for 3D bit data storage under two-photon excitation. Two-photon 3D bits recorded in photopolymerizable and photobleaching materials have demonstrated that recording densities could reach terabits per cubic centimeter; unfortunately both materials are not erasable. U.S. Patent No. 5,289,407 assigned to Cornell Research Foundation, Inc. discloses a method of 3D optical data storage in which a beam of coherent light is used to cause two-photon photopolymerization of a specimen gel to produce a bead of polymerised material in the gel which has a different refractive index from the surrounding gel material. However, this change is irreversible, and so the data bits are not erasable.

Photochromic materials that undergo a change in isomer states and photochromic polymers that produce a change in refractive-index upon two-photon excitation are both erasable materials. Another type of material that is of considerable interest is photorefractive material. The photorefractive effect results in a modulation of the refractive-index at the point of focus induced by the spatial distribution of electric charges upon illumination.

It has been discovered that such a change in the refractive index in photorefractive material may be reversed by illuminating the medium again with radiation to produce a uniform redistribution of the electric charges and erase the recorded information. However, this has previously only been achieved in a photorefractive crystals, e.g. lithium niobate (LiNbO_3), which are expensive to manufacture.

It is therefore desirable to provide a method of writing and erasing optical data in relatively inexpensive materials.

According to one aspect of the invention, there is provided a method of writing and erasing optical data comprising:

- producing a beam of focusable, coherent light;
- focussing the beam on a photorefractive polymeric material to cause two-photon excitation of the material at the focal point of the beam thereby modulating the refractive index at the focal point to record data; and
- illuminating the material with radiation to erase the recorded data.

According to another aspect of the invention there is provided a method of writing and re-writing optical data in a photorefractive polymeric material comprising:

- focussing a beam of coherent light on the photorefractive polymeric material to cause two-photon excitation of the material at the focal point of the beam thereby modulating the refractive index at the focal point to write data;
- illuminating the material with radiation to erase the recorded data;
- focussing another beam of coherent light on the photorefractive material to cause two-photon excitation of the material at the focal point of the beam

thereby modulating the refractive index at the focal point to re-write data in the photorefractive material.

- In the method of the present invention, the two-photon excitation produces a change in the spacial distribution of the electric charges at the focal point, thereby modulating the refractive index of the material at the focal point.

Preferably, the photorefractive polymeric material used in the method is such that illumination with electro-magnetic radiation in the ultraviolet (UV) or visible spectrum produces a uniform redistribution of the spacial distribution of the electric charges forming the data bits to erase the recorded data. The photorefractive polymer is preferably arranged to absorb radiation in only a narrow band in the UV to visible region of the electromagnetic spectrum. Creating a narrow absorption band will decrease the materials susceptibility to deterioration from the reading process or from incidental ultraviolet light (e.g. from sunlight).

- A laser may be used in a pulsed mode or a continuous wave laser may be used to write data by two-photon excitation of a photorefractive material. An ultrashort pulsed laser beam is typically used for two-photon excitation because the cooperative nature of two-photon excitation requires the use of a high peak power laser to produce efficient excitation. However, the use of an ultrashort pulse laser increases the cost of a recording device and makes it difficult to produce a compact system. We have also demonstrated that two-photon excitation under continuous wave (CW) illumination is possible. Although the average power needed for CW excitation is increased by approximately two orders of magnitude compared with ultrashort pulsed illumination, the use of continuous wave illumination can enable a fast, low cost, compact erasable two-photon 3D bit optical data storage system to be achieved.

The photorefractive material preferably includes a chromophore which provides absorption in the UV to visible region. The polymer may also be doped with a photosensitive material which provides absorption in the UV to visible region of the electromagnetic spectrum. In one embodiment, the polymer may comprise poly (N-vinylcarbazole) (PVK). In another preferred

embodiment, the polymer may comprise poly (methyl methacrylate) (PMMA). Each of these polymers may be doped with a photosensitive material, such as 2, 4, 7 - trinitro - 9 -fluorenone (TNF). One preferred chromophore is 2, 5 - dimethyl - 4 - (p - nitrophenylazo) anisole (DMNPAA) which also provides
5 absorption and an electro-optical effect in the UV to visible region. The polymeric material may also include a plasticiser, such as N-ethylcarbazole, (ECZ) to reduce the glass transition temperature of the material.

In the present invention, recorded bits of data may be read by employing a confocal microscope, a differential interference contrast (DIC) microscope
10 and/or a phase microscope utilising a source of coherent light of a wavelength on the edge of or outside the absorption band of the photorefractive polymeric material.

According to a further aspect of the invention there is provided a photorefractive polymeric material for use in a method of erasable optical data
15 storage, the photorefractive polymeric material providing absorption in the UV to visible region of the electromagnetic spectrum, wherein the absorption band of the photorefractive material is such as to enable the recording of bits of data by two photon excitation, the reading of the bits of data by a source of coherent light on the edge of or outside the absorption band, and the erasing of the bits of
20 data by illumination with radiation within the absorption band. The polymeric material preferably comprises a polymer, such as PVK or PMMA. The material may include a chromophore which provides absorption in the UV to visible region of the electromagnetic spectrum. Optionally, the polymer may also be doped with a photosensitive material which provides absorption in the UV to
25 visible region of the electromagnetic spectrum, and a plasticiser may be added to reduce the glass transition temperature of the material.

Preferably, a new photorefractive polymeric material in accordance with the second aspect of the invention includes at least some of the following materials in quantities falling substantially within the following ranges by
30 percentage of the total weight of the photorefractive polymeric material:

25% - 100% of a polymer, such as PVK or PMMA;

0% - 60% of a chromophore, such as DMNPAA;

— 0% - 5% of a photosensitive material, such as TNF; and

0% - 40% of a plasticiser, such as ECZ.

5 Preferred embodiments of the present invention using cheap photorefractive polymers as recording materials for rewritable/erasable 3D bit optical data storage under two-photon excitation to produce a high-density 3D optical data storage system will now be described by way of example only, with reference to the accompanying drawings, in which:-

10 Figure 1 is a graph showing the absorption curve of a photorefractive polymeric material for use in the present invention;

Figure 2 is a schematic diagram of a two-photon excitation microscope used to record data bits in a photorefractive polymer;

Figure 3(a) is a 24 x 24 bit pattern of the letter "C" recorded by two-photon excitation in a photorefractive polymer PVK upon its first reading;

Figure 3(b) is the same region after reading 500 times;

Figure 3(c) is a 24 x 24 bit pattern of the letter "A";

Figure 3(d) is the same region as Figure 3(c) after being exposed to UV illumination showing complete erasure of the recorded information;

20 Figure 4 shows recorded 24 x 24 bit patterns at different depths in the photorefractive polymer PVK using two-photon excitation;

Figure 4(a) shows a first layer including letter "A";

Figure 4(b) shows a second layer including letter "B" and

Figure 4(c) shows a third layer including letter "C";

25 Figure 5 (a) is a bit pattern of the letter "E" recorded by two-photon excitation in another photorefractive polymer (PMMA).

Figure 5 (b) is the same region as Figure 5(a) after being exposed to UV illumination showing erasure of the recorded information;

Figure 5(c) is a bit pattern of the letter "F" written into the same area as
30 Figures 1 and 2;

Figure 6 shows recorded bit patterns at different depths in the photorefractive polymer PMMA using two-photon excitation;

— Figure 6(a) shows a first layer including letter "A";

Figure 6 (b) shows a second layer including letter "B" and

5 Figure 6(c) shows a third layer including letter "C".

One example of a new photorefractive polymetric material that has been used to demonstrate rewritable/erasable 3D bit optical data storage is the polymer poly (*N*-vinylcarbazole (PVK) doped with the photosensitive material 2, 4, 7-trinitro-9-fluorenone (TNF) which provides absorption in the UV to
10 visible region of the spectrum. The photorefractive material also included, as a chromophore, 2, 5-dimethyl-4-(*p*-nitrophenylazo)anisole (DMNPAA) which also provides absorption in the UV to visible region. In this experiment compared with previous experiments the randomly oriented chromophores were not aligned by applying an electric field (poling) during polymerisation and
15 operation. Poling of the material requires the creation of a magnetic field across the surfaces of the polymer. Such a uniform magnetic field is difficult to maintain across the surface of a large polymer sample, increasing the complexity in fabricating the new photorefractive polymer. Finally *N*-ethylcarbazole (ECZ) was added to reduce the glass transition temperature of
20 the material. One preferred concentration of the materials DMNPAA:PVK:ECZ:TNF is 50:33:16:1 by percentage weight of the total weight of the photorefractive material although it will be appreciated that different proportions of the constituent materials may be used within the ranges specified above. Uniform films of thickness 100µm were fabricated by
25 combining all the materials in a teflon cast then polymerising the PVK at a temperature of 90°C over 2 days. The resulting polymer block was cut and polished to produce the sample used in the experiments.

Another example of a new photorefractive polymeric material that has
30 been used to demonstrate rewritable/erasable 3D bit optical data storage is the polymer poly (methyl methacrylate) (PMMA) doped with the photosensitive

material 2, 4, 7-trinitro-9-fluorenone (TNF) which provides absorption in the UV to visible region of the spectrum. The photorefractive material also included, as a chromophore, 2, 5-dimethyl-4-(p-nitrophenylazo)anisole (DMNPAA) which also provides absorption in the UV to visible region. In this experiment the randomly orientated chromophores were not aligned by applying an electric field (poling) during polymerisation and operation. Such a poling electric field is not necessary because the local electric field in the focus produced by a high numerical aperture objective is five orders of magnitude greater than that of the incident beam over the objective aperture. This local electric field is strong enough to induce a detectable electro-optic effect.

Finally N-ethylcarbazole (ECZ) was added to reduce the glass transition temperature of the material. One preferred concentration of the materials DMNPAA:PMMA:ECZ:TNF used was 10:73:16:1 by percentage weight of the total weight of the photorefractive material although it will be appreciated that different proportions of the constituent materials may be used within the ranges specified above. Uniform films of thickness 100µm were fabricated by combining all the materials in a teflon cast then polymerising the PMMA at a temperature of 65°C over 2 days. The resulting polymer block was cut and polished to produce the sample used in the experiments.

Figure 1 illustrates the absorption band of a 100µm thick sample of the new photorefractive polymeric materials based on PVK as detected in an Oriel UV-Vis spectrophotometer using a Xenon arc lamp source. The absorption band of the photorefractive polymeric material based on PMMA is almost identical.

It is seen from Figure 1 that the maximum of the absorption band of the new materials is within 380-600 nm. Therefore a laser beam of an infrared wavelength at 800 nm can be used in the recording process to produce two-photon excitation at 400 nm. The wavelength for recording may fall substantially within the range from about 750 nm to about 1200 nm. Since the absorption band cuts off approximately at a wavelength of 630 nm, a range of wavelengths from about 630 nm to about 1200 nm can be chosen to read out the

recorded photorefractive data bits without suffering from single-or two-photon excitation. Wavelengths above about 750 nm can be used provided the power of the reading beam is sufficiently low as not to cause single or two-photon excitation.

5 Referring to Figure 2, there is illustrated an optical system for two photon recording of bits of data in the photorefractive polymeric materials. The recording system comprises a laser (10), a mechanical shutter (11), linked to a computer (20), lenses (12, 13), a pin hole aperture (14), another aperture (16), and an objective lens (18). For reading with confocal geometry, the system also
10 includes a beam splitter (22), a further lens (24), another pin hole aperture (26) and a detector (28) also linked to the computer (20). A three-dimensional scanning stage (30) is provided for the mounting of the sample of photorefractive material (32). The scanning stage (30) is movable in the x, y and z directions under the control of the computer (20).

15 In the recording process, a Spectra-Physics Tsunami Ti:sapphire laser (10), was focused into the photorefractive polymer sample (32). The laser was used in a pulsed mode to record the bit patterns of Figures 3 and 4 in the PVK photorefractive polymeric material. In mode-locking operation, the laser can produce an ultrashort pulsed beam with a pulse width of 80 fs and an average
20 power of 800 mW. The laser was operated in a continuous wave (CW) mode to record the bit patterns of Figures 5 and 6 in the PMMA photorefractive polymeric material. In each case, the wavelength of the laser was tuned to 800 nm, which approximately corresponds to twice the wavelength of the main absorption band of the sample. From the absorption curve in Figure 1, we can
25 see that there will be no single-photon absorption at a wavelength of 800 nm; only the two-photon absorption can occur at a wavelength of 400 nm. The logic state of the recorded information was controlled by the mechanical shutter (11) linked to the computer (20). The recording material (32) was mounted upon a Melles Griot computer-controlled 3D translation stage (30). For recording, a
30 Zeiss Fluar objective (Figures 3 and 4) and an Olympus UPlanAPO objective

(Figures 5 and 6) (18) with numerical apertures of 0.75 and 0.70 respectively and magnification factors of 20 were used.

— For reading the change in refractive-index caused by the two-photon photorefractive effect an Olympus Fluo View microscope was employed and used in a differential interference contrast (DIC) mode. A He-Ne laser of wavelength 632.8 nm was coupled into the Fluo View for reading the recorded information, as the wavelength of 632.8 nm is on the edge of the absorption band and causes minimal damage to the recorded information (see Fig. 1). To erase the recorded information the region of interest was illuminated with the UV line of a mercury lamp in the Fluo View microscope. In both the reading and erasing an Olympus UPlanAPO objective (18) either with a numerical aperture of 0.7 and a magnification factor of 20 (Figures 3 and 4) or with a numerical aperture of 0.4 and a magnification factor of 10 (Figures 5 and 6) was used.

As a demonstration of the ability to record information as a change in refractive-index using two-photon excitation, Figures 3(a) and 3(b) show the measured change in refractive-index produced at the focus spots. In recording an average power of 5 mW at the focus spot was used to record the information. A pattern (the letter C) consisting of 24 x 24 bits was recorded in the sample. The bit separation was 3.2 μm , and the exposure time for each bit was 25 ms. In the reading process a laser beam of power less than 5mW was scanned across the sample to produce the DIC image. Figure 3(b) shows the deterioration of the recorded information after having been scanned 500 times. The contrast of the recorded bit in Figure 3(b) is 90% of that in Figure 3(a). This feature illustrates that there is a slight erasing of the information due to absorption of the light used for reading. The information recorded in Figure 3(c) used the same power and exposure time as used in Figure 3(a) and Figure 3(b). Figure 3(d) shows the same region as seen in Figure 3(c) after being exposed to the UV illumination for 1-2 seconds. The result shows the complete erasure of the previously recorded information.

Figure 4 demonstrates the ability of this system to record and read changes in refractive-index of multiple layers of information. Three layers of information were recorded with a layer separation of 10 μm . Each layer consists of a pattern of 24 x 24 bits. The first layer, recorded near the surface contains a pattern of the letter "A". The second and third layers consist of the letters "B" and "C" respectively, thus the achieved 3D data density was approximately 10 Gbits/cm³, which is comparable to that previously achieved in photochromic polymers, a photorefractive crystal and photobleaching materials.

Figure 5(a) shows the ability to record information as a change in refractive-index using continuous wave two-photon excitation. In recording an average power of 75 mW at the focus spot was used to record the information. A pattern (the letter E) consisting of 24 x 24 bits was recorded in the sample. The bit separation was 5.6 μm , and the exposure time for each bit was 2 ms. In the reading process a laser beam of power less than 5 mW was scanned across the sample to produce the DIC image. Figure 5(b) shows the same region as seen in Figure 5(a) after being exposed to the UV illumination for 1-2 seconds. The result shows the complete erasure of the previously recorded information. In Figure 5(c), a new pattern, the letter "F" is written into the same area as used in Figures 5(a) and 5(b). Two artifacts are marked with circles 1 and 2 in Figures 5(a), (b) and (c) showing that the same area was used to erase and rewrite information.

Figure 6 demonstrates the ability of this system to record and read changes in refractive-index of multiple layers of information. Three layers of information were recorded with a layer separation of 25 μm . Each layer consists of a pattern of 24 x 24 bits. The first layer, recorded near the surface contains a pattern of the letter "A". The second and third layers consist of the letters "B" and "C", respectively.

It will be seen from the above that the present invention provides an effective method of recording, reading, erasing and rewriting three dimensional data in relatively inexpensive photorefractive polymeric materials using either pulsed or continuous wave (CW) two-photon excitation to record and re-write

the data, and illuminating with radiation in the UV or visible region of the electromagnetic radiation to erase the recorded data.

— It will also be appreciated that various modifications, alterations and improvements may be made to the preferred embodiment described above without departing from the scope and spirit of the present invention. Such
5 modifications or improvements that are envisaged to increase the storage capacity of the system include the following:

1. The compensation of small amounts of cross talk between the layers (see Figure 4) due to spherical aberration from the refractive-index
10 mismatch between the recording material ($n = 1.75$) and the immersion medium ($n = 1$). The refractive-index mismatch results in an increase in the diffraction spot size at a deep position of a volume recording medium. As a result, a series of axial side peaks occur along the depth of the recording medium, thus resulting in cross talk between neighbouring data layers. It may be possible to
15 overcome this problem thereby increasing the density of data by using a variable tube length method.

2. Instead of the Ti:sapphire laser operated in CW mode, other types of continuous wave (CW) laser beams may be used to produce the two-photon excitation. For example, with the help of a 1.2 W CW laser diode, operated at a
20 near-infrared wavelength, a fast, low cost, compact, erasable two-photon 3D bit optical data storage system can be achieved.

3. Different photorefractive polymers may be used and the chemical properties of the materials may be modified to lead to an increase in the stability of the photorefractive polymer. By tailoring the absorption spectrum we can
25 determine the wavelength of light that will affect the material. Creating a narrow absorption band in the UV or visible region will decrease the materials susceptibility to deterioration due to irradiation from the reading process or from incidental UV light (i.e. sunlight).

4. A method for increasing the density of the two-photon data
30 storage system by utilising a recording method may be based on the polarisation state of the recording beam. This technique allows multiple bits to be recorded

- 12 -

at the same position within the material using different polarisation states of the recording beam, where upon reading, only the bits with an appropriate polarisation state are detected.

5. A method for selective bit erasure in the two-photon data storage system may be based on polarisation of the recording and reading beams. An individual bit can be selected and erased by changing the polarisation state of the recorded bit, so that it has an appropriate polarisation state which can either be detected or not detected upon reading.

CLAIMS

1. A method of writing and erasing optical data comprising:
 - producing a beam of focusable, coherent light;
focussing the beam on a photorefractive polymeric material to cause two-
- 5 photon excitation of the material at the focal point of the beam thereby modulating the refractive index at the focal point to record data; and
illuminating the material with radiation to erase the recorded data.
2. A method of writing and re-writing optical data in a photorefractive
- 10 polymeric material comprising:
 - focussing a beam of coherent light on the photorefractive polymeric material to cause two-photon excitation of the material at the focal point of the beam thereby modulating the refractive index at the focal point to write data;
illuminating the material with radiation to erase the recorded data;
- 15 focussing another beam of coherent light on the photorefractive polymeric material to cause two-photon excitation of the material at the focal point of the beam thereby modulating the refractive index at the focal point to re-write data in the photorefractive polymeric material.
- 20 3. A method according to claim 1 or claim 2 wherein the photorefractive material is illuminated with electro-magnetic radiation having a wavelength in the ultraviolet (UV) or visible spectrum to produce a redistribution of the spacial distribution of the electric charges forming bits of the data to erase the recorded data.
- 25 4. A method according to claim 3 wherein the photorefractive polymeric material is such that it absorbs radiation in only a narrow band in the UV to visible region of the electromagnetic spectrum.

- 14 -

5. A method according to claim 3 or claim 4 wherein the maximum of the absorption band of the photorefractive polymeric material falls substantially within the range from about 380nm to about 600 nm.
- 5 6. A method according to any one of claims 3 to 5 wherein the photorefractive polymeric material is such that it absorbs substantially no radiation above a wavelength of about 630 nm.
7. A method according to any one of the preceding claims wherein the data
10 recorded in the photorefractive polymeric material is read by illuminating the photorefractive polymeric material with coherent light of a wavelength falling substantially within the range from about 630 nm to about 1200 nm.
8. A method according to any one of the preceding claims wherein the
15 beam of focusable coherent light used to record data in the photorefractive material has a wavelength falling substantially within the range from about 750nm to about 1200 nm to cause two-photon excitation.
9. A method according to any one of the preceding claims wherein a pulsed
20 laser beam is used to record data in the photorefractive polymeric material.
10. A method according to any one of claims 1 to 8 wherein a continuous wave laser beam is used to record data in the photorefractive polymeric material.
- 25 11. A method according to any one of the preceding claims wherein a polarised beam of focusable, coherent light is used to record polarised bits of data in the photorefractive polymeric material.

- 15 -

12. A method according to claim 11 wherein different polarisation states of the recording beam are used to record multiple bits of data at the same position having different polarisation states in the photorefractive polymeric material.
- 5 13. A method according to claim 11 or claim 12 wherein bits of recorded data are read by using a reading beam having an appropriate polarisation state.
14. A method according to any one of claims 11 to 13 wherein individual bits of data are erasable by changing the polarisation state of the individual bits.
- 10 15. A method according to any one of the preceding claims wherein the photorefractive polymeric material includes at least about 25% of a polymer by percentage weight of the total weight of the photorefractive material.
- 15 16. A method according to any one of the preceding claims, wherein the photorefractive polymeric material includes a chromophore which provides absorption in the UV to visible region of the electromagnetic spectrum.
17. A method according to any one of the preceding claims wherein the
20 photorefractive polymeric material includes a photosensitive material which provides absorption in the UV to visible region of the electromagnetic spectrum.
18. A method according to any one of the preceding claims wherein the photorefractive polymeric material includes a plasticiser to reduce the glass
25 transition temperature of the material.
19. A method according to any one of the preceding claims wherein the photorefractive material includes at least some of the following materials in quantities falling substantially within the following ranges by percentage of the
30 total weight of the photorefractive material:

- 16 -

- 25% - 100% of a polymer ;
- 0%-60% of a chromophore;
- 0%-5% of a photosensitive material; and
- 0% - 40% of a plasticiser.

5

20. A method according to claim 15 or claim 19 wherein the polymer comprises poly (*N*-vinylcarbazole) (PVK).

21. A method according to claim 15 or claim 19 wherein the polymer
10 comprises poly (methyl methacrylate) (PMMA).

22. A method according to claim 16 or any one of claims 19 to 21 wherein the chromophore comprises 2, 5- dimethyl - 4 - (p-nitro-phenylazo) anisole (DMNPAA).

15

23. A method according to claim 17 or any one of claims 19 to 22 wherein the photosensitive material comprises 2, 4, 7-trinitro-9-fluorenone (TNF).

24. A method according to any one of claims 19 to 23 wherein the plasticizer
20 comprises *N*-ethylcarbazole (ECZ).

25. A photorefractive polymeric material for use in a method of erasable optical data storage, the photorefractive polymeric material providing absorption in the UV to visible region of the electromagnetic spectrum, wherein
25 the absorption band of the photorefractive material is such as to enable the recording of bits of data by two photon excitation, the reading of the bits of data by a source of coherent light on the edge of or outside the absorption band, and the erasing of the bits of data by illumination with radiation within the absorption band.

30

26. A photorefractive polymeric material according to claim 25 wherein the maximum of the absorption band of the photorefractive material falls substantially within the range from about 380 nm to about 600 nm.
- 5 27. A photorefractive polymeric material according to claim 25 or claim 26 wherein the upper end of the absorption band of the photorefractive polymeric material is about 630 nm.
- 10 28. A photorefractive polymeric material according to any one of claims 25 to 27 wherein the material includes at least about 25% of a polymer by percentage weight of the total weight of the photorefractive material.
- 15 29. A photorefractive polymeric material according to any one of claims 25 to 28 wherein the material includes a chromophore which provides absorption in the UV to visible region of the electromagnetic spectrum.
- 20 30. A photorefractive polymeric material according to claim 29 wherein the chromophore is present by an amount falling substantially within the range from about 0.5% to about 60% by percentage weight of the total weight of the material.
- 25 31. A photorefractive polymeric material according to any one of claims 25 to 30 wherein the material includes a photosensitive material which provides absorption in the UV to visible region of the electromagnetic spectrum.
- 30 32. A photorefractive polymeric material according to claim 31 wherein the photosensitive material is present by an amount falling substantially within the range from about 0.5% to about 5% by percentage weight of the total weight of the photosensitive material.

33. A photorefractive polymeric material according to any one of claims 25 to 32 wherein the material includes a plasticiser to reduce the glass transition temperature of the material.
- 5 34. A photorefractive polymeric material according to claim 33 wherein the plasticizer is present by an amount falling substantially within the range from 0% to about 40% by percentage weight of the total weight of the photorefractive polymeric material.
- 10 35. A photorefractive polymeric material for use in a method of optical data storage, wherein the material includes at least some of the following materials in quantities falling substantially within the following ranges by percentage of the total weight of the photorefractive polymeric material;
- 15 25% - 99.5% of a polymer;
 0% - 60% of a chromophore;
 0% - 5% of a photosensitive material; and
 0% - 40% of a plasticiser.
- 20 36. A photorefractive polymeric material according to claim 28 or claim 35 wherein the polymer comprises poly (*N*-vinylcarbazole) (PVK).
37. A photorefractive polymeric material according to claim 28 or claim 35 wherein the polymer comprises poly (methyl methacrylate) (PMMA).
- 25 38. A photorefractive polymeric material according to any one of claims 29, 30 or 35 to 37 wherein the chromophore comprises 2,5-dimethyl-4-(*p*-nitro phenylazo) anisole (DMNPAA).

39. A photorefractive polymeric material according to any one of claims 31, 32, or 35 to 38 wherein the photosensitive material comprises 2, 4, 7-trinitro-9-fluorenone (TNF).
- 5 40. A photorefractive polymeric material according to any one of claims 33 to 39 wherein the plasticiser comprises *N*-ethylcarbazole (ECZ).
41. A photorefractive polymeric material for use in a method of optical data storage comprising the following materials:
- 10 poly(*N*-vinylcarbazole) (PVK);
2,5, dimethyl-4-(*p*-nitrophenylazo) anisole (DMNPAA)
2,4,7-trinitro-9-fluorenone (TNF); and
N-ethylcarbazole (ECZ).
- 15 42. A photorefractive material according to claim 41 wherein the PVK;DMNPAA;TNF and ECZ are present in approximately the following concentrations by percentage weight of the total weight of the photorefractive material 33:50:1:16.
- 20 43. A photorefractive polymeric material for use in a method of optical data storage comprising the following materials:
- poly (methyl methacrylate) (PMMA);
2, 5, dimethyl-4-(*p*-nitrophenylazo) anisole (DMNPAA);
2,4,7-trinitro-9-fluorenone (TNF); and
25 *N*-ethylcarbazole (ECZ).
44. A photorefractive polymeric material according to claim 43 wherein the PMMA: DMNPAA; TNF and ECZ are present in approximately the following concentrations by percentage weight of the total weight of the photorefractive
30 polymeric material 73:10:1:16

AMENDED CLAIMS

[received by the International Bureau on 23 June 2000 (23.06.00);
original claims 1 – 44 replaced by new claims 1 – 45 (8 pages)]

1. A method of writing and erasing optical data comprising:
 - focussing light on a photorefractive polymeric material to cause two-photon excitation of the material at the focal point thereby modulating the refractive index at the focal point to record data; and
 - 5 illuminating the material with radiation to erase the recorded data.
2. A method of writing and re-writing optical data in a photorefractive polymeric material comprising:
 - 10 focussing light on the photorefractive polymeric material to cause two-photon excitation of the material at the focal point of the beam thereby modulating the refractive index at the focal point to write data;
 - illuminating the material with radiation to erase the recorded data;
 - focussing light on the photorefractive polymeric material to cause two-
 - 15 photon excitation of the material at the focal point thereby modulating the refractive index at the focal point to re-write data in the photorefractive polymeric material.
3. A method according to claim 1 or claim 2 wherein the modulation of the refractive index caused by the two-photon excitation is a refractive index inhomogeneity resulting from a non-uniform space-charge distribution within the region of excitation within the photorefractive polymeric material.
- 20
4. A method according to any one of claims 1 to 3 wherein the photorefractive material is illuminated with electro-magnetic radiation having a wavelength in the ultraviolet (UV) or visible spectrum to produce a redistribution of the spacial distribution of the electric charges forming bits of the data to erase the recorded data.
- 25

5. A method according to claim 4 wherein the photorefractive polymeric material is such that it absorbs radiation in only a narrow band in the UV to visible region of the electromagnetic spectrum.
- 5 6. A method according to claim 4 or claim 5 wherein the maximum of the absorption band of the photorefractive polymeric material falls substantially within the range from about 380nm to about 600 nm.
7. A method according to any one of claims 4 to 6 wherein the
10 photorefractive polymeric material is such that it absorbs substantially no radiation above a wavelength of about 630 nm.
8. A method according to any one of the preceding claims wherein the data
15 recorded in the photorefractive polymeric material is read by illuminating the photorefractive polymeric material with coherent light of a wavelength falling substantially within the range from about 630 nm to about 1200 nm.
9. A method according to any one of the preceding claims wherein the light
20 used to record data in the photorefractive material has a wavelength falling substantially within the range from about 750nm to about 1200 nm to cause two-photon excitation.
10. A method according to any one of the preceding claims wherein a pulsed
25 laser beam is used to record data in the photorefractive polymeric material.
11. A method according to any one of claims 1 to 9 wherein a continuous wave laser beam is used to record data in the photorefractive polymeric material.

12. A method according to any one of the preceding claims wherein polarised coherent light is used to record polarised bits of data in the photorefractive polymeric material.
- 5 13. A method according to claim 12 wherein different polarisation states of the recording beam are used to record multiple bits of data at the same position having different polarisation states in the photorefractive polymeric material.
- 10 14. A method according to claim 12 or claim 13 wherein bits of recorded data are read by using a reading beam having an appropriate polarisation state.
- 15 15. A method according to any one of claims 12 to 14 wherein individual bits of data are erasable by changing the polarisation state of the individual bits.
- 16 16. A method according to any one of the preceding claims wherein the photorefractive polymeric material includes at least about 25% of a polymer by percentage weight of the total weight of the photorefractive material.
- 20 17. A method according to any one of the preceding claims, wherein the photorefractive polymeric material includes a chromophore which provides absorption in the UV to visible region of the electromagnetic spectrum.
- 25 18. A method according to any one of the preceding claims wherein the photorefractive polymeric material includes a photosensitive material which provides absorption in the UV to visible region of the electromagnetic spectrum.
19. A method according to any one of the preceding claims wherein the photorefractive polymeric material includes a plasticiser to reduce the glass transition temperature of the material.

20. A method according to any one of the preceding claims wherein the photorefractive material includes at least some of the following materials in quantities falling substantially within the following ranges by percentage of the total weight of the photorefractive material:

5

- 25% - 100% of a polymer ;
- 0%-60% of a chromophore;
- 0%-5% of a photosensitive material; and
- 0% - 40% of a plasticiser.

10

21. A method according to claim 16 or claim 20 wherein the polymer comprises poly (*N*-vinylcarbazole) (PVK).

22. A method according to claim 16 or claim 20 wherein the polymer
15 comprises poly (methyl methacrylate) (PMMA).

23. A method according to claim 17 or any one of claims 20 to 22 wherein the chromophore comprises 2, 5- dimethyl - 4 - (p-nitro-phenylazo) anisole (DMNPAA).

20

24. A method according to claim 18 or any one of claims 20 to 22 wherein the photosensitive material comprises 2, 4, 7-trinitro-9-fluorenone (TNF).

25. A method according to any one of claims 20 to 24 wherein the plasticizer
25 comprises *N*-ethylcarbazole (ECZ).

26. A photorefractive polymeric material for use in a method of erasable optical data storage, the photorefractive polymeric material providing absorption in the UV to visible region of the electromagnetic spectrum, wherein
30 the absorption band of the photorefractive material is such as to enable the recording of bits of data by two photon excitation, the reading of the bits of data

by a source of coherent light on the edge of or outside the absorption band, and the erasing of the bits of data by illumination with radiation within the absorption band.

5 27. A photorefractive polymeric material according to claim 26 wherein the maximum of the absorption band of the photorefractive material falls substantially within the range from about 380 nm to about 600 nm.

28. A photorefractive polymeric material according to claim 26 or claim 27
10 wherein the upper end of the absorption band of the photorefractive polymeric material is about 630 nm.

29. A photorefractive polymeric material according to any one of claims 26 to 28 wherein the material includes at least about 25% of a polymer by
15 percentage weight of the total weight of the photorefractive material.

30. A photorefractive polymeric material according to any one of claims 26 to 29 wherein the material includes a chromophore which provides absorption in the UV to visible region of the electromagnetic spectrum.
20

31. A photorefractive polymeric material according to claim 30 wherein the chromophore is present by an amount falling substantially within the range from about 0.5% to about 60% by percentage weight of the total weight of the material.
25

32. A photorefractive polymeric material according to any one of claims 26 to 31 wherein the material includes a photosensitive material which provides absorption in the UV to visible region of the electromagnetic spectrum.

30 33. A photorefractive polymeric material according to claim 32 wherein the photosensitive material is present by an amount falling substantially within the

range from about 0.5% to about 5% by percentage weight of the total weight of the photosensitive material.

34. A photorefractive polymeric material according to any one of claims 26
5 to 33 wherein the material includes a plasticiser to reduce the glass transition temperature of the material.

35. A photorefractive polymeric material according to claim 33 wherein the
10 plasticizer is present by an amount falling substantially within the range from 0% to about 40% by percentage weight of the total weight of the photorefractive polymeric material.

36. A photorefractive polymeric material for use in a method of
15 erasable/rewritable optical data storage, wherein the material includes at least some of the following materials in quantities falling substantially within the following ranges by percentage of the total weight of the photorefractive polymeric material;

20 25% - 100% of a polymer;
0% - 60% of a chromophore;
0% - 5% of a photosensitive material; and
0% - 40% of a plasticiser.

37. A photorefractive polymeric material according to claim 29 or claim 36
25 wherein the polymer comprises poly (*N*-vinylcarbazole) (PVK).

38. A photorefractive polymeric material according to claim 29 or claim 36
wherein the polymer comprises poly (methyl methacrylate) (PMMA).

39. A photorefractive polymeric material according to any one of claims 30, 31 or 36 to 38 wherein the chromophore comprises 2,5-dimethyl-4-(p-nitro phenylazo) anisole (DMNPAA).
- 5 40. A photorefractive polymeric material according to any one of claims 32, 34 or 36 to 39 wherein the photosensitive material comprises 2, 4, 7-trinitro-9-fluorenone (TNF).
41. A photorefractive polymeric material according to any one of claims 34 10 to 40 wherein the plasticiser comprises *N*-ethylcarbazole (ECZ).
42. A photorefractive polymeric material for use in a method of erasable/rewritable optical data storage comprising the following materials:
- 15 poly(*N*-vinylcarbazole) (PVK);
2,5, dimethyl-4-(p-nitrophenylazo) anisole (DMNPAA)
2,4,7-trinitro-9-fluorenone (TNF); and
N-ethylcarbazole (ECZ).
43. A photorefractive material according to claim 42 wherein the 20 PVK;DMNPAA;TNF and ECZ are present in approximately the following concentrations by percentage weight of the total weight of the photorefractive material 33:50:1:16.
44. A photorefractive polymeric material for use in a method of optical data 25 storage comprising the following materials:
- poly (methyl methacrylate) (PMMA);
2, 5, dimethyl-4-(p-nitrophenylazo) anisole (DMNPAA);
2,4,7-trinitro-9-fluorenone (TNF); and
N-ethylcarbazole (ECZ).
- 30

45. A photorefractive polymeric material according to claim 44 wherein the PMMA: DMNPAA; TNF and ECZ are present in approximately the following concentrations by percentage weight of the total weight of the photorefractive polymeric material 73:10:1:16.




Figure 1.







Figure 2.




(a)



(b)




(c)




(d)


Figure 3.



(a)




(b)




(c)

Figure 4.




(a)

(b)




(c)


Figure 5.



(a)



(b)



(c)

Figure 6.

INTERNATIONAL SEARCH REPORT

International application No.
PCT/AU00/00117

A. CLASSIFICATION OF SUBJECT MATTER												
Int. Cl. ⁷ : G11B 7/00												
According to International Patent Classification (IPC) or to both national classification and IPC												
B. FIELDS SEARCHED												
Minimum documentation searched (classification system followed by classification symbols) IPC: AS ABOVE												
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched AU: IPC AS ABOVE												
Electronic data base consulted during the international search (name of data base and, where practicable, search terms used) WPAT, INTERNET, USPTO keywords: two photon excitation, polymer												
C. DOCUMENTS CONSIDERED TO BE RELEVANT												
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.										
X	US 5472759 (CHEN et al.) 5 December 1995	1 to 17, 25 to 29, and 31										
X	US 5289407 (STRICKLER et al.) 22 February 1994	1 to 17, 25 to 29, and 31										
X	US 5268862 (RENTZEPIS) 7 December 1993	1 to 17, 25 to 29, and 31										
<input checked="" type="checkbox"/> Further documents are listed in the continuation of Box C <input type="checkbox"/> See patent family annex												
<p>* Special categories of cited documents:</p> <table border="0"> <tr> <td>"A" document defining the general state of the art which is not considered to be of particular relevance</td> <td>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</td> </tr> <tr> <td>"E" earlier application or patent but published on or after the international filing date</td> <td>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone</td> </tr> <tr> <td>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</td> <td>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art</td> </tr> <tr> <td>"O" document referring to an oral disclosure, use, exhibition or other means</td> <td>"&" document member of the same patent family</td> </tr> <tr> <td>"P" document published prior to the international filing date but later than the priority date claimed</td> <td></td> </tr> </table>			"A" document defining the general state of the art which is not considered to be of particular relevance	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention	"E" earlier application or patent but published on or after the international filing date	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone	"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art	"O" document referring to an oral disclosure, use, exhibition or other means	"&" document member of the same patent family	"P" document published prior to the international filing date but later than the priority date claimed	
"A" document defining the general state of the art which is not considered to be of particular relevance	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention											
"E" earlier application or patent but published on or after the international filing date	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone											
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art											
"O" document referring to an oral disclosure, use, exhibition or other means	"&" document member of the same patent family											
"P" document published prior to the international filing date but later than the priority date claimed												
Date of the actual completion of the international search 9 March 2000		Date of mailing of the international search report 15 MAR 2000										
Name and mailing address of the ISA/AU AUSTRALIAN PATENT OFFICE PO BOX 200, WODEN ACT 2606, AUSTRALIA E-mail address: pct@ipaaustralia.gov.au Facsimile No. (02) 6285 3929		Authorized officer P. CLAYTON-STAMM Telephone No : (02) 6283 2168										

INTERNATIONAL SEARCH REPORT

International application No.

PCT/AU00/00117

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 9302454 (CORNELL RESEARCH FOUNDATION INC.) 4 February 1993	1 to 17, 25 to 29, and 31

INTERNATIONAL SEARCH REPORT

International application No.

PCT/AU00/00117

Box I Observations where certain claims were found unsearchable (Continuation of item 2 of first sheet)

This international search report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos :
because they relate to subject matter not required to be searched by this Authority, namely:
2. ☒ Claims Nos : 35
because they relate to parts of the international application that do not comply with the prescribed requirements to such an extent that no meaningful international search can be carried out, specifically:
Claim 35 is speculative and includes within its scope a polymer.
3. ☐ Claims Nos :
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a)

Box II Observations where unity of invention is lacking (Continuation of item 3 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

Claims 35, 41, 43 and 44 (and the claims appended to them) define polymer compositions for optical discs. Claim 1 defines a method for writing and erasing optical data using two photon excitation. This feature, at least, is absent from the above mentioned claims.

1. ☐ As all required additional search fees were timely paid by the applicant, this international search report covers all searchable claims
2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this international search report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☒ No required additional search fees were timely paid by the applicant. Consequently, this international search report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:
1 to 34, 36 to 40, and 42.

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest.
- ☐ No protest accompanied the payment of additional search fees.